

## PRODUCT DATA SHEET

# Sikalastic®-701

Polyurethane hybrid elastic top coat for liquid applied membrane waterproofing systems

### DESCRIPTION

Sikalastic®-701 is a 2-part, polyurethane hybrid, gloss finish top coat for Sika® Liquid Applied Membrane waterproofing systems.

### USES

Sikalastic®-701 may only be used by experienced professionals.

A gloss finish top coat for:

- Sika® Liquid Applied Membrane systems
- Sika® 2-C spray applied PU/PUA systems

For the following waterproofing system applications:

- Newly applied or renovating existing membranes
- Flat and pitched roof structures
- Communal walkways
- Podium decks
- Terrace roofs
- For exterior use only

### CHARACTERISTICS / ADVANTAGES

- Aliphatic polyurethane providing UV and yellowing resistance
- Good long term weathering performance
- Good colour stability and gloss retention
- Good chemical resistance
- Low soiling and easily cleanable
- Suitable for cool roofs by providing a high Solar Reflective Index
- Resistant to ponding water

### APPROVALS / CERTIFICATES

- CE Marking and Declaration of Performance to European Technical Assessment ETA-20/0248, based on ETAG 005 Part 1 and Part 6 — Liquid applied roof waterproofing kits. Part 1: General. Part 6: Specific stipulations for Kits based on Polyurethane
- Fire Testing EN 13501-1, Sikalastic®-701, Sikalastic®-702, Warringtonfire, Report No.19896B
- Fire Testing EN 13501-5, Sikalastic®-612, BRE, Report No.Q100536-1001
- Fire Testing EN 13501-5, Sikalastic®-614, BRE, Report No.Q100536-1003
- Abrasion resistance AR0.5(Special), Sikalastic®-614/701, FACE, Test report No. FC/18/8048
- Abrasion resistance AR0.5(Special), Sikalastic®-701, Sikalastic®-702, FACE, Test report No. FC/18/8048

### PRODUCT INFORMATION

<b>Composition</b>	Elastomeric Polyurethane/Hybrid	
<b>Packaging</b>	Part A	10,0 kg container
	Part B	2,5 kg container
	Part A + B	12,5 kg ready to mix unit
	Refer to current price list for packaging variations	
<b>Shelf life</b>	12 months from date of production	
<b>Storage conditions</b>	Store properly in original, unopened and undamaged packaging, in dry	

#### PRODUCT DATA SHEET

Sikalastic®-701

November 2022, Version 01.01

020915505000000013

conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.

<b>Colour</b>	<b>Final colour</b>	White
	The product can be coloured locally with Sika® In Pail Tinting (IPT) machines. For more information, consult the local Sika customer service.	
<b>Density</b>	~1,25 kg/l (mixed A+B) Value at +23 °C	(DIN EN ISO 2811-11)
<b>Solid content by mass</b>	Part A	~67 %
	Part B	~100 %
<b>Solid content by volume</b>	Part A	~55 %
	Part B	~100 %

## TECHNICAL INFORMATION

<b>Tensile strength</b>	<b>Temperature</b>	<b>Value</b>	(EN ISO 527-3)
	+23 °C	~10 MPa	
	-20 °C	~20 MPa	
<b>Tensile strain at break</b>	<b>Temperature</b>	<b>Value</b>	(EN ISO 527-3)
	+23 °C	~100 %	
	-20 °C	~20 %	
<b>Solar reflectance</b>	Initial Solar Reflectance	0,88	(ASTM C1549)
<b>Thermal emittance</b>	Initial Thermal Emittance	0,86	(ASTM C1371)
<b>Solar reflectance index</b>	Initial SRI (Convective Coefficient, Medium Wind)	~112	
<b>Chemical resistance</b>	Resistant to many chemicals. Contact Sika Technical Service for additional information.		
<b>External fire performance</b>	Broof T1 / Broof T4		(prEN 1187)
<b>Reaction to fire</b>	Euroclass E		(EN 13501-1)

## SYSTEM INFORMATION

<b>System structure</b>	<p>Sikalastic®-701 can be used with the following:</p> <p><b>1-Part PU cold applied Systems</b></p> <ul style="list-style-type: none"><li>▪ Sikalastic®-612</li><li>▪ Sikalastic®-614</li><li>▪ Sikalastic®-618</li></ul> <p><b>2-Part Aromatic PU/PUA cold applied Systems</b></p> <ul style="list-style-type: none"><li>▪ Sikalastic®-702</li></ul> <p><b>2-Part PU/PUA hot spray applied Systems</b></p> <ul style="list-style-type: none"><li>▪ Sikalastic®-851 R</li><li>▪ Sikalastic®-838 R</li><li>▪ Sikalastic®-835 I</li></ul> <p>Refer to the following System Data Sheets:</p> <ul style="list-style-type: none"><li>▪ SikaRoof® PUR</li><li>▪ SikaRoof® MTC</li><li>▪ SikaRoof® PUA Roof Waterproofing Systems</li></ul>
-------------------------	--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

## APPLICATION INFORMATION

<b>Mixing ratio</b>	Part A : Part B = 80 : 20 (by volume)
---------------------	---------------------------------------

<b>Yield</b>	~0,25 kg/m <sup>2</sup> to 0,30 kg/m <sup>2</sup> applied in a single coat				
<b>Ambient air temperature</b>	+2 °C min. / +40 °C max.				
<b>Relative air humidity</b>	Above +20 °C	35 % min / 80 % max.			
	Below +20 °C	45 % min. / 80 % max.			
<b>Dew point</b>	Beware of condensation. The substrate and uncured applied membrane must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the membrane finish.				
<b>Substrate temperature</b>	+2 °C min. / +40 °C max.				
<b>Substrate moisture content</b>	Refer to Product Data Sheet of the appropriate base layers				
<b>Pot Life</b>	1 hour at +20 °C Pot life will decrease at higher temperatures and increase at lower temperatures.				
<b>Tack free time</b>	<b>Condition</b>	<b>Property</b>	<b>Value</b>	(EN 29117:1992)	
	20 °C / 50 % RH	Tack free time	~45 minutes		
	20 °C / 50 % RH	Hard drying time	~60 minutes		
	20 °C / 50 % RH	Final drying time	~90 minutes		
	<b>Condition</b>	<b>Property</b>	<b>Value</b>	(EN 29117:1992)	
	5 °C / 50 % RH	Tack free time	~75 minutes		
	5 °C / 50 % RH	Hard drying time	~105 minutes		
	5 °C / 50 % RH	Final drying time	~135 minutes		
	Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.				
<b>Applied product ready for use</b>	<b>Temperature</b>	<b>Relative Humidity</b>	<b>Rain Resistant</b>	<b>Foot Traffic</b>	<b>Full Cure</b>
	+10 °C	50 %	~75 minutes	~150 minutes	~1 day
	+20 °C	50 %	~60 minutes	~120 minutes	~1 day
	+30 °C	50 %	~45 minutes	~90 minutes	~16 hours
	Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.				

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

- Sika Method Statement: Sikalastic®-834 R

## IMPORTANT CONSIDERATIONS

Installation work must only be carried out by Sika® trained and approved contractors, experienced in this type of application.

- Products must only be applied in accordance with their intended use.
- Do not use for indoor applications.
- Do not apply near to running air intakes of air conditioning units. Switch off units before applying.
- Do not dilute with any solvent or water.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

Confirm waiting /overcoating time has been achieved on the previously applied system base layer. The base layer must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and loose material. If dust exists on the surface, it must be completely removed before application of the product, preferably by vacuum extraction equipment.

If the maximum overcoating time of the base layer is exceeded, the surface must be lightly abraded using light abrasive manual tools or mechanical equipment to roughen the surface. Depending on the type of base layer, a solvent wipe may also be required. Finally, completely remove all the dust by vacuum extraction equipment.

### MIXING

Prior to mixing all parts, mix separately Part A (resin) using an electric single or double paddle mixer and stirrer (300 to 400 rpm) or other suitable equipment. Mix liquid and all the coloured pigment until a uniform colour / mix has been achieved. Add Part B (hardener) to Part A and mix Part A + B continuously for 3,0 minutes until a uniformly coloured mix has been achieved. Mix full units only. Mixing time for A+B = ~3,0 minutes.

### APPLICATION

Apply mixed product in 1 coat by roller, brush or spray equipment to achieve a consistent thickness and required surface finish.

### CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically or with a proprietary paint stripper.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika (Cambodia) Ltd.

Legacy Business Center, Building #29  
street 245  
Sangkat Tuol Tom Poug 2, Khan  
Chamkarmorn  
12308, Phnom Penh, Cambodia  
Tel: +855 23 901 450

#### PRODUCT DATA SHEET

Sikalastic®-701  
November 2022, Version 01.01  
020915505000000013