

PRODUCT DATA SHEET

SikaGrind®-874 KH

EFFICIENT GRINDING AID AND PERFORMANCE ENHANCER FOR THE CEMENT

DESCRIPTION

SikaGrind®-874 KH is a chloride free liquid cement grinding aid with performance enhancing properties. SikaGrind®-874 KH has been specifically designed to increase the output of cement grinding plants and obtain improved strength development for cements with high amount of clinker replacements.

USES

- Improve the production rate of the cement grinding system.
- Increase the strength of the cement.

CHARACTERISTICS / ADVANTAGES

SikaGrind®-874 KH is a dispersant with the following characteristics:

- Neutralisation of electrical charges on the surface of the cement particles
- Separation of the cement particles

SikaGrind®-874 KH provides the following advantages in the cement production:

- Enhanced grinding properties of the cement mill due to less accumulation of material on grinding balls and mill-liners
- Higher separator efficiency due to improved cement particle dispersion
- Reduced relative power consumption per ton of cement due to increased output of the grinding system (tons per hour)
- Easier achievement of the desired cement fineness (Blaine, particle fraction > 32µm, granulometry) due to reduced re-agglomeration of the sufficiently ground cement particles
- Minimized problems with “plugging” due to improved powder flow characteristics

SikaGrind®-874 KH gives the following advantages to the finished cement:

- Reduced quantity of “over-milled” particles in the cement granulometry
- Easier discharge of the silos
- Increased strengths
- Economic cement design with clinker replacements

PRODUCT INFORMATION

| | |
|---------------------|--|
| Composition | Aqueous polymers solution |
| Packaging | 1000 kg |
| Appearance / Colour | Brown liquid |
| Shelf life | At least 12 months in undamaged, unopened and sealed original containers when stored at temperatures between +5 °C and +35 °C. |
| Storage conditions | Protect from frost, direct sunlight and contamination. |
| Density | 1.040 – 1.100 kg/l (at +20 °C) |

APPLICATION INFORMATION

Recommended dosage Typical dosage rates of SikaGrind®-874 KH are between 0.2–0.5 kg per

ton of cement (0.02 %–0.05 % of total weight = cement clinker + additions).

The optimum dosage to achieve the desired characteristics shall be determined in Plant trials.

Influencing factors are e.g. the properties of clinker source, type of cement and other plant variables. For consistent results, SikaGrind®-874 KH must be accurately dispensed.

Compatibility

Cements treated with SikaGrind®-874 KH are compatible in concretes produced with all commercial admixtures including air entrainers, water reducers, retarders and superplasticizers. The performance of concrete admixtures is not adversely affected by the use of SikaGrind®-874 KH.

Dispensing

SikaGrind®-874 KH is added onto the clinker feed shortly before the mill entrance or directly into the grinding mill (first or second compartment). Suitable dosage pumps with adjustable flow rates shall be used for accurate dosing.

Note: Periodically, the end of the additive tube/hose shall be checked to ensure that it is not blocked.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

ECOLOGY, HEALTH AND SAFETY

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must

Sika (Cambodia) Ltd.

Legacy Business Center, Building #29
street 245
Sangkat Tuol Tom Pong 2, Khan
Chamkarmorn
12308, Phnom Penh, Cambodia
Tel: +855 23 901 450

SikaGrind-874KH-en-KH-(07-2021)-1-1.pdf

PRODUCT DATA SHEET

SikaGrind®-874 KH
July 2021, Version 01.01
021407021000000657

