

PRODUCT DATA SHEET

SikaGrind®-175 Activator

EFFICIENT GRINDING AID AND PERFORMANCE ENCHANCER FOR THE CEMENT

DESCRIPTION

SikaGrind[®] - 175 Activator is a chloride free liquid cement griniding aid with performance enchancing properties. SikaGrind[®] - 175 Activator has been specifically designed to increase the output of cement grinding plants and obtain improved strength development for cements with high amount of clinker replacements.

USES

- Improve the production rate of the cement griniding system.
- Increase the strength of the cement.

CHARACTERISTICS / ADVANTAGES

SikaGrind®-175 Activator is a dispersant with the following characteristics:

- Neutralisation of electrical charges on the surface of the cement particles
- Separation of the cement particles

SikaGrind [®] -175 Activator provides the following advantages in the cement production:

- Enhanced grinding properties of the cement mill due to less accumulation of material on grinding balls and mill-liners
- Higher separator efficiency due to improved cement particle dispersion
- Reduced relative power consumption per ton of cement due to increased output of the grinding system(tons per hour)
- Easier achievement of the desired cement fineness (Blaine, particle fraction > 32μm, granulometry) dueto reduced re-agglomeration of the sufficiently ground cement particles
- Minimized problems with "plugging" due to improved powder flow characteristics

SikaGrind $^{\circledR}$ -175 Activator gives the following advantages to the finished cement:

- Reduced quantity of "over-milled" particles in the cement granulometry
- Easier discharge of the silos
- Increased strengths
- Economic cement design with clinker replacements

PRODUCT INFORMATION

Composition	Aqueous polymer solution
Packaging	1000 kg
Shelf life	At least 12 months in undamaged, unopened and sealed original containers when stored at temperatures between +5 °C and +35 °C.
Storage conditions	Protect from frost, direct sunlight and contamination.
Appearance and colour	Brown liquid
Density	1.093 – 1.097 kg/l (at +25 °C)

APPLICATION INFORMATION

Recommended dosage	Typical dosage rates of SikaGrind®-175 Activator are between 0.2–0.5 kg per ton of cement (0.02 %–0.05 % of total weight = cement clinker + additions). The optimum dosage to achieve the desired characteristics shall be determined in Plant trials. Influencing factors are e.g. the properties of clinker source, type of cement and other plant variables. For consistent results, SikaGrind®-175 Activator must be accurately dispensed.
Dispensing	SikaGrind®-175 Activator is added onto the clinker feed shortly before the millentrance or directly into the grinding mill (first or second compartment). Suitable dosage pumps with adjustable flow rates shall be used for accurate dosing. Note: Periodically, the end of the additive tube/those shall be checked to ensure that it is not blocked.
Compatibility	Cements treated with SikaGrind®-175 Activator are compatible in concretes produced with all commercial admixtures including air entrainers, water reducers, retarders and superplasticizers. The performance of concrete admixtures is not adversely affected by the use of SikaGrind®-175 Activator.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

Sika (Cambodia) Ltd.

Legacy Business Center, Building #29 street 245 Sangkat Tuol Tom Poung 2, Khan Chamkarmorn 12308, Phnom Penh, Cambodia

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaGrind-175Activator-en-KH-(02-2023)-1-1.pdf

